




**REFRACTORY STUDS:  
RECTANGULAR THREE TINE**

<b>To order or specify give:</b>				
Product	Size:	Length:	Tine Length:	Material:
Code:	Specify	Specify	Specify	Specify
<b>RA R-31</b>	<b>1/8 x 5/8</b>	<b>L</b>	<b>TL</b>	



<i>STUD</i>			
MIN L	MIN BL	MIN TL	FERRULE CODE
2-1/4	1-1/4	1	R265

<b>MATERIAL</b>	<b>MILD STEEL</b> C - 0.23% max. P - 0.04% max. Mn - 0.90% max. S - 0.05% max.	<b>STAINLESS STEEL</b> AISI grade - 304 standard Other grades available upon request.
<b>MECHANICAL PROPERTIES</b>	Tensile ..... 60,000 psi (min.) Yield ..... 50,000 psi (min.) Elongation ..... 20% (in 2 inches)	Values for various grades available upon request.
<b>PLATING</b>	Plating is not standard. Cadmium, Copper, Nickel, and Zinc available upon customer request.	Does not apply to Stainless.

[www.sunbeltstudwelding.com](http://www.sunbeltstudwelding.com)

**Sunbelt Stud Welding, Inc.**  
 6381 Windfern Road  
 Houston, Texas 77040-4915



**1-800-462-9353**  
**713-939-8903**  
**fax 713-939-9013**