




REFRACTORY STUDS: RECTANGULAR TWO TINE

To order or specify give:

Product	Size:	Length:	Tine Length:	Material:
Code:	Specify	Specify	Specify	Specify
RA R-2T	1/8 x W	L	TL	



<i>STUD</i>					
W	SW	MIN L	MIN BL	MIN TL	FERRULE CODE
3/8	1/8	1-1/4	1/4	1"	R375
5/8	5/32	1-1/4	5/8	5/8	R625

MATERIAL	MILD STEEL C - 0.23% max. P - 0.04% max. Mn - 0.90% max. S - 0.05% max.	STAINLESS STEEL AISI grade - 304 standard Other grades available upon request.
MECHANICAL PROPERTIES	Tensile 60,000 psi (min.) Yield 50,000 psi (min.) Elongation 20% (in 2 inches)	Values for various grades available upon request.
PLATING	Plating is not standard. Cadmium, Copper, Nickel, and Zinc available upon customer request.	Does not apply to Stainless.

www.sunbeltstudwelding.com

Sunbelt Stud Welding, Inc.
 6381 Windfern Road
 Houston, Texas 77040-4915



1-800-462-9353
713-939-8903
 fax **713-939-9013**