




**REFRACTORY STUDS: SPLIT PIN**

**To order or specify give:**  
 Product Code: **RA SP** Diameter: Specify **D** Length: Specify **L** Material: Specify



STUD		
D	MIN L	FERRULE CODE
3/16	7/8	P250
1/4	7/8	P312
5/16	7/8	P375

<b>MATERIAL</b>	<b>MILD STEEL</b> C - 0.23% max. P - 0.04% max. Mn - 0.90% max. S - 0.05% max.	<b>STAINLESS STEEL</b> AISI grade - 3021/304/305 std. Other grades available upon request.
<b>MECHANICAL PROPERTIES</b>	Tensile .....60,000 psi (min.) Yield .....50,000 psi (min.) Elongation.....20% (in 2 inches)	Values for various grades available upon request.
<b>PLATING</b>	Plating is not standard. Cadmium, Copper, Nickel, and Zinc available upon customer request.	Does not apply to Stainless.

[www.sunbeltstudwelding.com](http://www.sunbeltstudwelding.com)

Sunbelt Stud Welding, Inc.  
 6381 Windfern Road  
 Houston, Texas 77040-4915



1-800-462-9353  
 713-939-8903  
 fax 713-939-9013