




REFRACTORY STUDS: "Y" ANCHOR

To order or specify give:

Product Code: **RA Y** Diameter: Specify **1/4** Length: Specify **L** Material: Specify



| STUD | |
|------------------|-------------------------|
| MIN L | FERRULE CODE |
| 2-7/16 | RA250 |

Studs shorter than L MIN will have no bends.

| | | |
|----------------------------------|--|---|
| MATERIAL | MILD STEEL C - 0.23% max. P - 0.04% max. Mn - 0.90% max. S - 0.05% max. | STAINLESS STEEL AISI grade - 304/310/316/330 std. Other grades available upon request. |
| MECHANICAL PROPERTIES | Tensile 60,000 psi (min.) Yield 50,000 psi (min.) Elongation 20% (in 2 inches) | Values for various grades available upon request. |

www.sunbeltstudwelding.com

Sunbelt Stud Welding, Inc.
 6381 Windfern Road
 Houston, Texas 77040-4915



11-11

1-800-462-9353
713-939-8903
fax 713-939-9013