




CD STUDS: NON FLANGED

To order or specify give:
 Product Code: **CD NF** Diameter: Specify **D** Length: Specify **L** Material: Specify



STUD		
D	MAX BD	MIN L
4-40	.115	.250
6-32	.142	.250
8-32	.168	.250
10-32	.194	.250
10-24	.194	.250
1/4-20	.254	.375
5/16-18	.317	.500

MATERIAL	MILD STEEL C - 0.23% max. P - 0.04% max. Mn - 0.90% max. S - 0.05% max.	STAINLESS STEEL AISI grade - 304/305 std. Other grades available upon request.
MECHANICAL PROPERTIES	Tensile 60,000 psi (min.) Yield 50,000 psi (min.)	Tensile..... 85,000 psi (min.) Yield 40,000 psi (min.)
PLATING	Copper plating is standard	Does not apply to Stainless.
ANNEALING	Studs are annealed where required	Studs are annealed where required
MATERIAL	ALUMINUM Alloy 1100 & 5000 Series Other alloys available upon request	BRASS Alloy (lead free) 70 - 30 std. Other alloys available upon request
MECHANICAL PROPERTIES	Values for various alloys available upon request	Tensile..... 70,000 psi (min.) Yield 50,000 psi (min.)

www.sunbeltstudwelding.com

Sunbelt Stud Welding, Inc
6381 Windfern Road
Houston, Texas 77040-4915



1-800-462-9353
713-939-8903
fax 713-939-9013