




ARC STUDS: BENT COLLAR

To order or specify give:

Product Code:	Base Diameter:	Base Length:	Thread Diameter:	Thread Length:	Material: Specify
ARC B-COL	Specify BD	Specify BL	Specify TD	Specify TL	



STUD						
D	STD. TL	BD	MIN BL	CD	CT	X
3/8-16	1.375	.331	.625	5/8	.109	5/8

THREADS: Standard thread is UNC-2A (Rolled when possible), other threads are available upon request.

MATERIAL	MILD STEEL		STAINLESS STEEL
	C - 0.23% max.	P - 0.04% max.	AISI grade - 302/304/305/316 std. Other grades available upon request.
MECHANICAL PROPERTIES	Tensile	60,000 psi (min.)	Values for various grades available upon request.
	Yield	50,000 psi (min.)	
	Elongation	20% (in 2 inches)	
PLATING	Plating is not standard. Cadmium, Copper, Nickel, and Zinc available upon customer request.		Does not apply to Stainless.

www.sunbeltstudwelding.com

Sunbelt Stud Welding, Inc.
 6381 Windfern Road
 Houston, Texas 77040-4915



1-800-462-9353
713-939-8903
fax 713-939-9013