




ARC STUDS: EYEBOLT

To order or specify give:
 Product Diameter: Length: Eye Dia.: Gap: Material:
 Code: **ARC EB** Specify **D** Specify **L** Specify **ID** Specify **G** Specify



STUD					
D	MIN L	MIN BL	MIN ID	MIN G	FERRULE CODE
3/16	1-7/8	3/4	1/2	3/16	F187
1/4	1-3/4	3/4	3/4	1/4	F250
5/16	1-7/8	3/4	3/4	5/16	F312
3/8	2-5/8	1	7/8	3/8	F375
7/16	3	1-1/8	1	7/16	F437
1/2	3-5/8	1-3/8	1-1/4	1/2	F500

MATERIAL	MILD STEEL C - 0.23% max. Mn - 0.80% max. P - 0.04% max. S - 0.05% max.	STAINLESS STEEL AISI grade - 302/304/305/316 std. Other grades available upon request.
MECHANICAL PROPERTIES	Tensile 80,000 psi (min.) Yield 50,000 psi (min.) Elongation..... 20% (in 2 inches)	Values for various grades available upon request.
PLATING	Plating is not standard, Cadmium, Copper, Nickel, and Zinc available upon customer request.	Does not apply to Stainless.

www.sunbeltstudwelding.com

Sunbelt Stud Welding, Inc.
 6381 Windfern Road
 Houston, Texas 77040-4915



9-25

1-800-462-9353
713-939-8903
 fax **713-939-9013**