




ARC STUDS: LONG REDUCED BASE

To order or specify give:
 Product Code: **ARC** Diameter: Specify **L** Length: Specify **L** Material: Specify **LRB** **D** **L**



STUD						
D	MIN L	BD	MIN BL	FD	FH	FERRULE CODE
1/4	3/4	.187	.375	.281	.109	FS187
5/16	3/4	.250	.375	.359	.125	FS250
3/8	3/4	.312	.375	.437	.125	FS312
7/16	1	.375	.375	.500	.140	FS375
1/2	1	.437	.437	.578	.140	FS437
5/8	1-1/4	.500	.500	.656	.156	FS500
3/4	1-1/2	.625	.718			FS625

Standard thread is UNC-2A (Rolled when possible).
 Other threads are available upon request. Maximum standard thread length is 3-7/8".

MATERIAL	MILD STEEL	STAINLESS STEEL	
	C - 0.23% max. Mn - 0.90% max.	P - 0.04% max. S - 0.05% max.	AISI grade - 302/304/305/316 std. Other grades available upon request.
MECHANICAL PROPERTIES	Tensile	60,000 psi (min.)	Values for various grades available upon request.
	Yield	50,000 psi (min.)	
	Elongation	20% (in 2 inches)	
PLATING	Plating is not standard. Cadmium, Copper, Nickel, and Zinc available upon customer request.	Does not apply to Stainless.	

www.sunbeltstudwelding.com

Sunbelt Stud Welding, Inc
 6381 Windfern Road
 Houston, Texas 77040-4915



1-800-462-9353
713-939-8903
 fax **713-939-9013**