




ARC STUDS: NO THREAD

To order or specify give:
 Product Code: Diameter: Specify Length: Specify Material: Specify
ARC NT D L Material: Specify



STUD				
D	MIN L	FD	FH	FERRULE CODE
3/16	3/4	.281	.093	F187
1/4	3/4	.359	.109	F250
5/16	3/4	.437	.109	F312
3/8	3/4	.500	.125	F375
7/16	3/4	.578	.140	F437
1/2	7/8	.627	.156	F500
5/8	1"	.796	.187	F625
3/4	1-1/8	.937	.250	F750
7/8	1-1/4	1.093	.312	F875
1"	1-1/2	1.312	.375	F1,000

* Ferrules used with Studs 3/4" long are special "short F" ferrules. **KNOCK-OFF studs are available if shorter lengths are required.

MATERIAL	MILD STEEL C - 0.23% max. Mn - 0.90% max. P - 0.04% max. S - 0.05% max.	STAINLESS STEEL AISI grade - 302/304/305/316 std. Other grades available upon request.
MECHANICAL PROPERTIES	Tensile 60,000 psi (min.) Yield 50,000 psi (min.) Elongation..... 20% (in 2 inches)	Values for various grades available upon request.
PLATING	Plating is not standard. Cadmium, Copper, Nickel, and Zinc available upon customer request.	Does not apply to Stainless.

www.sunbeltstudwelding.com

Sunbelt Stud Welding, Inc.
 6381 Windfern Road
 Houston, Texas 77040-4915



1-800-462-9353
713-939-8903
fax 713-939-9013