




ARC STUDS: RECTANGULAR PLAIN

To order or specify give:
 Product Code: **ARC R-** Size: **1/8** x Length: Specify **L** Material: Specify
PL **W**



STUD					
W	MIN L	FW	FL	FH	FERRULE CODE
3/8	7/8	.218	.437	.125	R375
5/8	1"	.218	.687	.156	R625

MATERIAL	MILD STEEL C - 0.23% max. Mn - 0.90% max. P - 0.04% max. S - 0.05% max.	STAINLESS STEEL AISI grade - 302/304/305/316 std. Other grades available upon request.
MECHANICAL PROPERTIES	Tensile 80,000 psi (min.) Yield 50,000 psi (min.) Elongation..... 20% (in 2 inches)	Values for various grades available upon request.
PLATING	Plating is not standard. Cadmium, Copper, Nickel, and Zinc available upon customer request.	Does not apply to Stainless.

www.sunbeltstudwelding.com

Sunbelt Stud Welding, Inc
 6381 Windfern Road
 Houston, Texas 77040-4915



1-800-462-9353
713-939-8903
 fax **713-939-9013**