




ARC STUDS: SHORT REDUCED BASE

To order or specify give:
 Product Code: **ARC** Diameter: Specify **D** Length: Specify **L** Material: Specify **SRB**



STUD						
D	MIN L	BD	MIN BL	FD	FH	FERRULE CODE
1/4	7/8	.187	.156	.281	.109	TB250
5/16	7/8	.275	.250	.390	.109	RB312
3/8	7/8	.312	.250	.437	.125	RB375
1/2	1	.435	.250	.593	.156	RB500
5/8	1-1/8	.500	.312	.887	.156	TB625
3/4	1-1/8	.625	.375	.812	.187	TB750

Standard thread is UNC-2A (Rolled when possible).
 Other threads are available upon request. Maximum standard thread length is 3-7/8".

MATERIAL	MILD STEEL	STAINLESS STEEL
	C - 0.23% max. Mn - 0.90% max.	P - 0.04% max. S - 0.05% max.
MECHANICAL PROPERTIES	Tensile 80,000 psi (min.) Yield 50,000 psi (min.) Elongation..... 20% (in 2 inches)	Values for various grades available upon request.
PLATING	Plating is not standard. Cadmium, Copper, Nickel, and Zinc available upon customer request.	Does not apply to Stainless.

www.sunbeltstudwelding.com

Sunbelt Stud Welding, Inc.
 6381 Windfern Road
 Houston, Texas 77040-4915



9-7

1-800-462-9353
713-939-8903
fax 713-939-9013