




ARC STUDS: SHOULDER NO THREAD

To order or specify give:
 Product Code: Diameter: Length: Ext. Dia.: Ext. Length: Material:
ARC SH-NT Specify **D** Specify **L** Specify **ED** Specify **EL** Specify



STUD						
D	MIN L	ED	EL	FD	FH	FERRULE CODE
5/16	3/8	3/16	3/16	.437	.109	F312
3/8	3/8	3/16	3/16	.500	.125	F375
1/2	1/2	3/8	45/64	.627	.156	F500

MATERIAL	MILD STEEL		STAINLESS STEEL
	C - 0.23% max. Mn - 0.90% max.	P - 0.04% max. S - 0.05% max.	AISI grade - 302/304/305/316 std. Other grades available upon request.
MECHANICAL PROPERTIES	Tensile	60,000 psi (min.)	Values for various grades available upon request.
	Yield	50,000 psi (min.)	
	Elongation.....	20% (in 2 inches)	
PLATING	Plating is not standard. Cadmium, Copper, Nickel, and Zinc available upon customer request.		Does not apply to Stainless.

www.sunbeltstudwelding.com

Sunbelt Stud Welding, Inc.
 6381 Windfern Road
 Houston, Texas 77040-4915



1-800-462-9353
713-939-8903
 fax **713-939-9013**