




ARC STUDS: STANDARD THREAD

To order or specify give:
 Product Code: **ARC ST** Diameter: Specify **D** Length: Specify **L** Material: Specify



ARC STUD						
D	MIN L	BD	MIN BL	FD	FH	FERRULE CODE
1/4	3/4	.215	.375	.312	.093	P250
5/16	3/4	.275	.375	.406	.109	P312
3/8	3/4	.330	.390	.468	.109	P375
7/16	3/4	.387	.437	.531	.125	P437
1/2	7/8	.446	.500	.593	.156	P500
5/8	1	.562	.625	.750	.187	P625
3/4	1-1/4	.680	.796	.920	.250	P750
7/8	1-3/8	.798	.859	1.046	.312	P875
1"	1-1/2	.913	.921	1.187	.375	P1,000

MATERIAL	MILD STEEL		STAINLESS STEEL
	C - 0.23% max. Mn - 0.90% max.	P - 0.04% max. S - 0.05% max.	AISI grade - 302/304/305/316 std. Other grades available upon request.
MECHANICAL PROPERTIES	Tensile	60,000 psi (min.)	Values for various grades available upon request.
	Yield	50,000 psi (min.)	
	Elongation.....	20% (in 2 inches)	
PLATING	Plating is not standard. Cadmium, Copper, Nickel, and Zinc available upon customer request.		Does not apply to Stainless.

www.sunbeltstudwelding.com

Sunbelt Stud Welding, Inc.
 6381 Windfern Road
 Houston, Texas 77040-4915



1-800-462-9353
713-939-8903
fax 713-939-9013